SPECIFICATION FOR SILICONE BASED RESIN COMBINATION FOR VACCUM PRESSURE IMPREGNATION (VPI) {(SILICON IMPREGNATING RESIN AND ITS FILLER/AUXILIARY MATERIAL (IF ANY)} OF 3-PHASE TRACTION MOTOR TYPE 6FRA- 6068 & 6FXA-7059 OF ELECTRIC LOCOMOTIVES

Approved by

CEE/TM

SPECIFICATION FOR SILICONE BASED RESIN COMBINATION FOR VACCUM PRESSURE IMPREGNATION (VPI) {(SILICON IMPREGNATING RESIN AND ITS FILLER/AUXILIARY MATERIAL (IF ANY)} OF 3-PHASE TRACTION MOTOR TYPE 6FRA-6068 & 6FXA-7059.

CHITTARANJAN LOCOMOTIVE WORKS, WEST BENGAL, INDIA

NO.: 4TMS.096.093 DATE: 31/05/2021 Page 1 of 6

Prepared by

Lee 31/05/302

SSE/TMDC

Reviewed by

DY.CEE/TMD

ALT NO.	AUTHORITY	DESCRIPTION	INITIAL	DATE
• •				
				,

SPECIFICATION FOR SILICONE BASED RESIN	CHITTARANJAN	
COMBINATION FOR VACCUM PRESSURE	LOCOMOTIVE WORKS, P	age 2 of 6
IMPREGNATION (VPI) {(SILICON IMPREGNATING	WEST BENGAL, INDIA	
RESIN AND ITS FILLER/AUXILIARY MATERIAL (IF	NO.: 4TMS.096.093	
ANY)} OF 3-PHASE TRACTION MOTOR TYPE 6FRA-6068 & 6FXA-7059.	DATE: 31/05/2021	
Prepared by	Reviewed by	`
21105 13021	hy 2/2	
SSE/TMDO	DY.CEE/TMD	

1.0 SCOPE

This specification covers the technical requirement of Silicone based resin combination for vacuum pressure impregnation (VPI) {(Silicon Impregnating Resin and its Filler/Auxiliary material (if any)} to be used for Vacuum pressure impregnation for H- and C- class insulation of 3-phase traction motor type 6 FRA6068/6FXA7059. The material shall comply with this specification instructions in chemical composition, mechanical properties and all other listed requirements.

2.0 GENERAL

- 2.1SILICON IMPREGNATING RESIN FOR VPI OR EQUIVALENT TO SILRES H62C is a methylphenylvinylhydrogenpolysiloxane not modified with organic components, very low volatility (Suitable for vacuum Pressure impregnation), cured by heat through catalysed addition cross linking without the formation of cleavage products, it also cures in thick layers, even in contact with air, tack free and without formation of bubbles. It is remarkably insensitive during curing to influence of various kinds of insulating materials. It contains no decomposable and problematic The vulcanise of **SILICON** physiologically components. OR EQUIVALENT TO SILRES H62C IMPREGNATING RESIN FOR VPI conforms to the fire safety requirements defined in UL 94 V0.
- 2.2 Filler /Auxiliary material is a liquid component of Silicone Impregnating Resin for VPI or Equivalent, which cured by heat through catalyzed addition cross linking without the formation of cleavage products, it also cures in thick layers, even in contact with air, tack free and without formation of bubbles. It is remarkably insensitive during curing to influence of various kinds of insulating materials. The Mixture contains no decomposable and physiologically problematic components. This instruction lays down all the requirements which are made for substance filler material.

Auxiliary material is a liquid component of Silicone Impregnating mixture.

- 2.3 Ratio to be used in VPI
- (a) Silicon Impregnating Resin or Equivalent 110 parts by weight
- (b) Filler/ Auxiliary material (if any) 02 parts by weight

SPECIFICATION FOR SILICONE BASED RESIN **CHITTARANJAN** COMBINATION FOR VACCUM PRESSURE Page 3 of 6 LOCOMOTIVE WORKS, IMPREGNATION (VPI) {(SILICON IMPREGNATING WEST BENGAL, INDIA RESIN AND ITS FILLER/AUXILIARY MATERIAL (IF NO.: 4TMS.096.093 ANY)} OF 3-PHASE TRACTION MOTOR TYPE 6FRA-DATE: 31/05/2021 6068 & 6FXA-7059. Reviewed by Prepared by 31105/2021 DY.CEE/TMD SSE/TMDO

3.0 REQUIREMENTS

$3.1\,$ Gel times for SILICON IMPREGNATING RESIN FOR VPI OR EQUIVALENT TO SILRES H62C

Temperature	Gelling Time
140° C	300 min
160° C	100 min
180° C	45 min
200° C	26 min
220° C	15 min

3.2 Filler/ Auxiliary Material (If any)

General Characteristics	Unit	Values	Test Method
Refractive index at 20°C		1.467±0.003	DIN 53491
Storage life from delivery date	Months	12	IEC 455-2
in original airtight container at			Section 14
room temperature (≤25°C)			

4. Product data (Cured for 16 Hrs at 150°C)

Typical General Characteristics	Inspection Method	Value	
Appearance	Visual	Clear, Transparent	
Density at 25°C		1.16 g/cm^3	
Hardness Shore D	DIN 53505	60-80	
Flexural strength at 25°C	DIN EN ISO 178	2440N/mm ²	
Thermal conductivity at 50°C	DIN 52612	0.2 W/km	
Specific heat at 0-100°C		1.45 j/(g.K)	
Volume resistivity ρ , at 23°C	IEC 60093, (=DIN 53482)	$1.5 \times 10^{15} \Omega$ cm	
Dielectric strength(50Hz) at 23°C	IEC 60243-1	27 kV/mm	
a) Surrounding medium: electrical			
insulating mineral oil			
Dielectric strength(50Hz) at 23°C	IEC 60243-1	82 kV/mm	
b) Surrounding medium: silicone			
rubber(SIR)	• .		

SPECIFICATION FOR SILICONE BASED RESIN		CHITTARANJAN	
COMBINATION FOR VACCUM PRESSURE		LOCOMOTIVE WORKS,	Page 4 of 6
IMPREGNATION (VPI) {(SILICON IMPREGNATING		WEST BENGAL, INDIA	
RESIN AND ITS FILLER/AUXILIARY MATERIAL (IF		NO.: 4TMS.096.093	
ANY)} OF 3-PHASE TRACTION MOTOR TYPE 6FRA-6068 & 6FXA-7059.		DATE: 31/05/2021	
Prepared by		Reviewed by	N
Dele (2021		or only	`
SSE/TMDO		DY.CEE/TMD	

4.1 Special Tests

Sealed Tube Test set up (for testing reactions with	IEC 60038-18-22
other insulating items)	
VPI of Test sample with Vacuum and Temp Control	For BDV after VPI

All the test specified in the specification shall be carried out preferably at manufacturer's works. The manufacturer shall arrange all the necessary

machinery, apparatus, labour and assistance required for conducting the tests without Extra cost. If any testing facility is not available at firm's premises, the test has to be done from any Govt. approved NABL lab at own (Firm's) cost.

APPLICATION

5.0 Silicone based resin combination for vacuum pressure impregnation (VPI) {(Silicon Impregnating Resin and its Filler/ Auxiliary material (if any)} to be used for Vacuum pressure impregnation for C- classinsulation of 3-phase traction motor type 6 FRA6068 / 6FXA7059.

6.0 REFERENCE TO ABB STANDARDS

This specification is equivalent to ABB specification HZN: 02582 & HZN: 02583 for the item Silicon Impregnating Resin or Equivalent and HZLK:605002 for Filler/ Auxiliary material (if any)

7.0 SHELF LIFE

Shelf life of the material in the original sealed drum at a room temperature 25°C should be \geq 09 months for Silicon Impregnating Resin or Equivalent and \geq 12 months for Filler/ Auxiliary material (if any).

SPECIFICATION FOR SILICONE BASED RESIN **CHITTARANJAN** COMBINATION FOR VACCUM PRESSURE LOCOMOTIVE WORKS, Page 5 of 6 IMPREGNATION (VPI) {(SILICON IMPREGNATING WEST BENGAL, INDIA RESIN AND ITS FILLER/AUXILIARY MATERIAL (IF NO.: 4TMS.096.093 ANY)} OF 3-PHASE TRACTION MOTOR TYPE 6FRA-DATE: 31/05/2021 6068 & 6FXA-7059. Prepared by Reviewed by 31105 19021 SSE/TMDO DY.CEE/TMD

8.0 PACKING

The material shall be supplied in Drum of 20/25/180/200kg. The material shall be suitably packed so as to ensure safe transportation of material without any damage.

9.0 MARKING

The material shall be labelled securely and indelibly (e.g with an adhesive label on an appendage) with the following information –

- a) Name of the manufacturer, purchase order reference and date.
- b) Name, quantity, batch no., date of manufacture & expiry date of the material.
- c) Special precaution for storage, if applicable for the material.

10.0 SPECIAL INSTRUCTION

If any deviation in properties of product data, firm may seek approval of the same submitting detail justification regarding gelling time, viscosity, colour, ratio etc. Firm should submit detail VPI procedure of their product along with offer. Firm should submit Compatibility Test report of their product vs Existing Silicone based resin combination for vacuum pressure impregnation (VPI) before prototype inspection indicating that there will be no adverse effect on existing insulation scheme.

SPECIFICATION FOR SILICONE BASED RESIN COMBINATION FOR VACCUM PRESSURE IMPREGNATION (VPI) {(SILICON IMPREGNATING RESIN AND ITS FILLER/AUXILIARY MATERIAL (IF ANY)} OF 3-PHASE TRACTION MOTOR TYPE 6FRA-6068 & 6FXA-7059.

CHITTARANJAN LOCOMOTIVE WORKS, WEST BENGAL, INDIA NO.: 4TMS.096.093 DATE: 31/05/2021

Page 6 of 6

Prepared by

SSE/TMDO

Reviewed by

DY.CEE/TMD